



Martin Resources

P.O. Box 191
Kilgore, TX 75663
(903) 983-6287
(903) 983-6215

ANALYSIS OF ELEMENTAL SULFUR PASTILL

FOR INDUSTRIAL USE

SULFUR (S)	99.9 +
BTU	6650
MOISTURE	0.09
ACIDITY as H₂SO₄	Trace, less than 0.0001
SELENIUM (Se)	Less than 0.0001
TELLURIUM (Te)	Less, than 0.0001
ARSENIC (As)	Trace, less than 0.0001
IRON (Fe)	0.0010
CLORIDE (Cl)	Less then 0.001
ASH	0.0032
ORGANIC IMPURITIES	0.0076
<hr/>	
PARTICLE SIZE	100% through 5 mesh Less than .3 through -16
DENSITY	70 LBS/ft³